

# gloveon

## Maverick LC

### Nitrile Exam Gloves Powder Free, Standard Cuff



GloveOn® Maverick LC is a worthy addition to the Maverick family. The all-rounder glove is thicker with an extended cuff to suit situations which require greater protection.



Physical Dimensions		
Length (mm)	≥ 280	
Palm Thickness (mm)	0.09 ± 0.02	
Finger Thickness (mm)	0.14 ± 0.02	
Physical Properties		
	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 500
Elongation after Isopropanol immersion (%)	≥ 500	N/A
Inspection Levels & AQL		
	Inspection Level	AQL
Watertightness	G1	1.5
Physical Dimensions	S2	4.0
Tensile Strength	S2	4.0
Visual Inspection (Major)	S4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove

#### REORDER CODE

NTR26XS	X-SMALL
NTR26SS	SMALL
NTR26MM	MEDIUM
NTR26LL	LARGE
NTR26XL	X-LARGE
NTR26XXL	XX-LARGE

#### FEATURES

- Fingertip textured • Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested • Ambidextrous
- Standard cuff • Aqua blue colour

#### PACKAGING

100 gloves per box for XS to XL  
80 gloves per box for XXL  
10 boxes per carton

#### REGULATORY COMPLIANCE

ARTG 164563, FDA 510(k), MDD 93/42/EEC, REACH, ROHS Directive 2002/95/EC, EU 10/2011, EC 1935/2004, EU 2016/425

#### STANDARDS

ASTM D6319, ASTM D5151, ASTM D6124, ASTM D6978, EN ISO 374-1 (Type B), EN 374 part 2, 4 & 5, EN 16523-1, EN 420, EN 455 part 1, 2, 3 & 4, EN 1186, EN 13130, CEN/TS 14234, ISO 10993 part 5 & 10, HACCP Certified

#### MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05-Test Report PN 101567)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	15.1 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.00mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	30.8 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

**WARNING:** Carmustine and Thiotepa, at the tested concentration, degraded Maverick LC nitrile glove at 15.1 minutes and 30.8 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Measured breakthrough time (minutes)	>10	>30	>60	>120	>240	>480
Permeation performance level	1	2	3	4	5	6

Chemical	EN 16523-1:2015 Permeation Level	EN 374-4:2013 Mean Degradation (%)
J n-Heptane	3	33.9
K 40% Sodium Hydroxide	6	-19.9
P 30% Hydrogen Peroxide	2	34.5
T 37% Formaldehyde	6	-11.0

A brand by



**Mun Australia**  
Toll free: 1800 456 837  
munglobal.com.au



Proud Supporter of  
Birthing Kit Foundation (Australia)



Protection Always On